

Process

Name of the process	Short liner repair processes
Type of curing	cold, warm or UV curing
Impregnation	On-site manually

General

Sewing integration	Jersey / Fringe
Sewing fineness	7
Width	350 mm (DN 100) 430 mm (DN 125) 520 mm (DN 150) 1 300 mm standard
Weight per unit area	1 081 g/m ² +/- 7,2 % 1 387 g/m ² +/- 7,2 %
Thickness	1,78 mm +/- 6 %

Construction	Weight per unit area [g/m ²]		Tolerance [+/- %]	Material [DIN 1259-1]	Fineness of rope [tex]
	1 081	1 387			
Upside					
	1 081	1 387			
0°	331	384	5	ECR-glas	1 200
90°	288	384	5	ECR-glas	600
CSM	450	600	10	ECR-glas	
Bottom					
	1 081	1 387		1 081	1 387
Sewing thread	12	19	5	PES 110 dtex	PES 167 dtex

Date: 22.01.2019
DW